






TEST REPORT

Test Report No.: B202405100005		Page 1 of 2
		Issue Date 21/05/2024
Customer/Manufacturer Name:	AMAZING FLOORS E-42 IST FLOOR MANGOLPURI INDUSTRIAL AREA PHASE -II NEW DELHI 110034	
Item Description:	RUBBER TILE	
Sample Condition:	OK	
Identification:	RUBBER TILE	
Sample Deposited/Collected by:	- AT LAB	
Ref no	NIL	
Date of receipt:	10/05/2024	
Date(s) of performance of tests:	10/05/2024 TO 21/05/2024	
Test Location:	At lab	
Test specification(s):	AS PER PARTY SPECIFICATION	
General Environmental Conditions:	Temperature: 27°C ± 2°C; Relative Humidity: 65 ± 5%RH	
Result:	The product conforms the relevant specification	
Supplementary Information:	- Deviation from the test methods as prescribed in relevant Specification/Work Instructions: N/A - The information supplied by the customer may affect the validity of results reported as per standard requirement.	
Remarks: Nil		
<i>This report is related to the sample submitted.</i>		
Tested by:	Approved by:	Issued by:
		
ANALYST	REVIEW	TM/Authorized Signatory
Date: 21/05/2024	Date: 21/05/2024	Date: 21/05/2024



TEST REPORT

Test Report : B202405100005
No.

Page : 2 of 2

Dated : 21/05/2024

<u>S NO.</u>	<u>TEST PARAMETERS</u>	<u>TEST RESULTS</u>	<u>TEST METHOD</u>
1.	Tensile Strength (Mpa)	1.5	IS:3400(P-1)2012
2.	% elongation at break	121	IS:3400(P-1)2012
3.	Density, kg/m ³	982	IS:3400(P-9)2012
4.	Specific gravity	0.99	ASTM D 792-13
5.	Impact Resistance	No failure	ASTM D 1709-98
6.	Hardness, shore A	63	ASTM D 2240-05
7.	Abrasion Resistance,% by weight	0.8	IS:1237-2012
8.	Compression set,%24 hours at 27±1°C	96.9	IS:3400(P-10)2012
9.	Temperature Resistance test at 40°C	No changes	BTH/STP/BM02
10.	Temperature Resistance test at 100°C	No changes	BTH/STP/BM02
11.	Temperature Resistance test at 150°C	No changes	BTH/STP/BM02
12.	Compression set %	18.2	IS 3400 PART 11
13.	Skid Resistance (Dry Condition)	40	ASTM E 303
14.	Ground Electrical Resistance,M Ohm	168	ASTM F 150

*****END OF REPORT*****



BHUMI TEST HOUSE

109/7, Phirni Road, Mundka, New Delhi-110041, T.: 9910541479, 8376926426
E.: a2btllab@gmail.com, bth0422@gmail.com | info.bhumitesthouse@gmail.com
W.: www.bhumitesthouse.in

(1) The above result are related only to the test performed on the sample. Endorsement of product is neither inferred nor implied.
(2) This report is not to be reproduced wholly or in part forbidden to be used as an evidence in the court of law & ought not to be used in any advertising media without our special permission in writing. (3) Sample will be destroyed after 15 & 30 days from the date of reporting unless otherwise specified. (4) Total liability of our test house is limited to the invoiced amount. (5) Report refers to the sample received by us.